

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

**0 352 855
A2**

12

EUROPEAN PATENT APPLICATION

21 Application number: 89201924.1

51 Int. Cl.4: **C23F 11/14**

22 Date of filing: 21.07.89

30 Priority: 29.07.88 IT 2155288
23.12.88 IT 2309488

43 Date of publication of application:
31.01.90 Bulletin 90/05

64 Designated Contracting States:
AT BE CH DE ES FR GB GR LI LU NL SE


71 Applicant: **ENIRICERCHE S.p.A.**
Corso Venezia 16
I-20121 Milan(IT)

72 Inventor: **Cesari, Marco**
Via Ravenna 10/A
I-20097 San Donato Milanese Milan(IT)
Inventor: **Roggero, Arnaldo**
Via Libertà 72
I-20097 San Donato Milanese Milan(IT)
Inventor: **Rivola, Luigi**
Via Moro 21
I-20097 San Donato Milanese Milan(IT)
Inventor: **Demertzis, Yean**
Via Breno 4
I-20139 Milan(IT)

74 Representative: **Roggero, Sergio et al**
Ing. Barzanò & Zanardo Milano S.p.A. Via
Borgonuovo 10
I-20121 Milano(IT)

54 Inhibitors of corrosion in high-strength and medium-strength steels.

57 A method is disclosed for the inhibition of general corrosion, and of stress corrosion by hydrogen sulfide in manganese and low-alloy, medium-strength and high strength steels, obtained by means of the use of compounds of formula:



EP 0 352 855 A2

INHIBITORS OF CORROSION IN HIGH-STRENGTH AND MEDIUM-STRENGTH STEELS

The present invention relates to a method for inhibiting the corrosion in manganese and low-alloy, medium-strength and high-strength steels.

Corrosion, due to its nature of process of decay of metal materials used for building structures and production facilities, causes enormous direct and indirect damages.

In particular, the corrosion of steels commonly used in petrochemical industry, besides in the facilities for production, extraction and transport of gas and petroleum represents a serious problem, because the normal corrosive action of water and of oxygen is potentiated and speeded up by the presence of carbon dioxide, as well as of organic and inorganic salts and acids.


Stress corrosion in the presence of hydrogen sulfide (SSC), frequently observed in petroleum extraction facilities, is particularly serious. Furthermore, it is known that in buried metal structures colonies of sulfate-reducing bacteria may develop under anaerobic conditions, with the relevant production of hydrogen sulfide.

The resulting embrittlement (besides the general corrosion) in these steels, which simultaneously undergo mechanical stresses of considerably high value, results often in cracking and microcracking of the material, and is the cause of serious risks of failure and of mechanical collapse.

Although a large number of inhibitors of general corrosion are known, no evidence exists of effective inhibitors of stress corrosion caused by hydrogen sulfide in high-strength or medium-strength, manganese and low-alloy steels. What is more, these steel types are very largely used for building structures undergoing stresses and such severe use conditions as described, and the use of inhibitors would offer an improvement in the margins of safety in the calculation of the structures, as well as a considerable reduction in costs.

The present Applicant has now surprisingly found that some azomethynes exert an effective protective action towards the general corrosion and the embrittlement caused by hydrogen sulfide (SSC) in high-strength or medium-strength steels of P-110 and X-70 type.

In accordance therewith, the present invention relates to a method for inhibiting the general corrosion and the stress embrittlement caused by hydrogen sulfide (SSC), both in the presence and in the absence of CO₂, of manganese and low-alloy steels having different mechanical strength, used in the systems for drilling, producing, transporting and processing gas and petroleum, characterized in that an organic substance selected from among the group consisting of those substances as defined by the general formula:



wherein:

R₁ and R₂, which may be equal to, or different from, each other, are a straight or branched, saturated or unsaturated, either substituted or non-substituted hydrocarbon chain of from 1 to 30 carbon atoms, or a one-ring or condensed two-ring, aromatic or heteroaromatic radical;

\overline{m} is either 0 or 1; and

\overline{n} is a numeral comprised within the range of from 1 to 30,

is added to the aggressive aqueous-organic mixture into contact with said systems.

In the present invention, by "compounds defined by the formula (I)", both the substance in pure form, and a mixture of such compounds, whether monomeric or polymeric, contained in the reaction mixture, are meant.

For the purposes of the present invention, a preferred group of compounds of formula (I) comprises those compounds in which R₁ and R₂, the one independently from the other one, represent an aliphatic radical with an either straight or branched chain, containing from 1 to 30 carbon atoms, and, possibly, one or more unsaturations, or a one-ring or condensed two-ring hetero-aromatic radical.

A more preferred group comprises those compounds of formula (I) in which R₁ and R₂, the one independently from the other one, represent an aliphatic radical with an either straight or branched chain, containing from 1 to 30 carbon atoms, or a condensed two-ring heteroaromatic radical.

The compounds of formula (I) are prepared according to methods known from classic chemistry for the preparation of the Schiff bases. Said compounds are typically prepared by means of the condensation of an aldehyde with an amine.

When \overline{m} is 0, the substances can be prepared by means of the condensation of an aldehyde of formula (II):



with an amine of formula

H_2N-R_2 .

When m is 1, the substances can be prepared by means of the condensation of an amine of formula $H_2N-(CH_2)_n-NH_2$ with at least one aldehyde of formula (II).

5 R_1 , R_2 and n are as hereinabove defined for the general formula (I).

In practice, the reaction is carried out according to traditional methods, by causing the two starting compounds to react with each other in the presence of an inert, high-boiling organic solvent.

10 In order to be used as corrosion inhibitors, such compounds, or the mixture of said compounds of both monomeric and polymeric character, contained in the reaction mixture, are generally added, in an amount comprised within the range of from 1 to 500 ppm, to the aqueous-organic mixture into contact with the steel structures.

Such an amount will be preferably comprised within the range of from 5 to 200 ppm, and still more preferably it will be comprised within the range of from 15 to 100 ppm.

15 The temperature of usage of the compounds according to the present invention is not critic, and very good results were obtained within the temperature range of from 0 to 180 °C.

The following examples which are given for the only purpose of better illustrating some representative aspects of the present invention should not be interpreted as being limitative of the scope of the same invention.

20

Examples 1-10

25 The compounds of the Examples from 1 to 10, whose structure is reported in Table I, were prepared according to the general method as herein reported in the following:

The amine of formula

H_2N-R_2

(0.10 eq) for the Examples from 1 to 4, and the amine of formula

$H_2N-(CH_2)_n-NH_2$

30 for the Examples from 5 to 10, is charged to a three-necked flask (of 250 ml of capacity), equipped with thermometer, magnetic stirring means, and with the adaptor for a dripping funnel and a distiller.

The amine is then diluted with toluene (100 ml). To this solution, maintained with stirring, a solution (100 ml) containing a stoichiometric amount of the aldehyde

R_1-CHO

35 in toluene is added dropwise.

The reaction mixture is then heated until toluene is completely distilled off; then the vacuum of a water vacuum pump is applied, the reaction mixture is progressively heated up to a temperature of 250-300 °C, and is finally maintained 2 hours at this maximum temperature value.

The I.R. analysis of the so obtained products confirmed the assigned structures.


40


45

50

55

Table 1



Example No.	R ₁	R ₂	m	n
1	CH ₃	CH ₃ -(CH ₂) ₇ -	0	-
2	CH ₃	CH ₃ -(CH ₂) ₁₁ -	0	-
3	CH ₃ -(CH ₂) ₂ -	CH ₃ -(CH ₂) ₇ -	0	-
4	CH ₃ -(CH ₂) ₁₁ -		0	-
5	CH ₃ -(CH ₂) ₂ -	CH ₃ -CH ₂ -	1	3
6	CH ₃ -(CH ₂) ₂ -	CH ₃ -CH ₂ -	1	6
7	CH ₃ -(CH ₂) ₉ -	CH ₃ -(CH ₂) ₉ -	1	3
8	CH ₃ -(CH ₂) ₉ -	CH ₃ -(CH ₂) ₉ -	1	4
9	CH ₃ -(CH ₂) ₉ -	CH ₃ -(CH ₂) ₉ -	1	12
10	CH ₃ -(CH ₂) ₃ -	CH ₃ -(CH ₂) ₃ -	1	8

Examples 11-20

In order to evaluate the effect of corrosion inhibition, the corrosion currents and the hydrogen permeation currents were measured on specimens in the absence and in the presence of inhibitors.

More particularly, specimens of API 5L X70 steel of blade shape with 1 mm of thickness are dipped into standard aqueous solutions containing acetic acid (0.5%) and sodium chloride (5%) saturated with hydrogen

sulfide, and not containing any inhibitors (Example 11), or containing 25 ppm of a compound according to the Examples from 1 to 9 (respectively Examples from 12 to 20).

The results are reported in the following Table.

Table 2

Example No.	Compound of Example No.	i_{corr} , $\mu A/cm^2$	i_{perm} , $\mu A/cm^2$
11	-	372.3	6.9
12	1	4.2	0.88
13	2	6.2	0.16
14	3	4.2	1.08
15	4	5.0	0.25
16	5	3.2	0.74
17	6	3.4	0.75
18	7	10.0	2.7
19	8	4.28	2.45
20	9	4.8	0.92

The decrease in the corrosion rate and in the permeation current, with the consequent decrease in hydrogen concentration inside the steel, confirm the effect of inhibition of the general corrosion performed by the compounds according to the instant invention.

Example 21

In order to evaluate the effect of inhibition of the stress corrosion by hydrogen sulfide, a corrosion test was developed according to the standards described in NACE Standard TM/01/77 on specimens of medium-high strength steel.

In particular, specimens of API 5L X70 steel, prepared according to the Standard Test TM/01/77, are put under stress under constant load equal to 95% of yielding strength inside standard aqueous solutions containing acetic acid (0.5%) and sodium chloride (5%), saturated with hydrogen sulfide; one of said solutions does not contain any inhibitors, whilst the other solutions contain 25 ppm of each one of the compounds of Examples from 1 to 9.

Whilst in the solution not containing inhibitors, after about 10 hours the fracture occurs of the tested specimen, in the other solutions, containing the compounds of Examples from 1 to 9 as the inhibitors, after 720 hours no fractures were observed.

Example 22

The standard corrosion test according to the standards as described in NACE Standard TM/01/77 was furthermore carried out according to the same method as reported in Example 21 on specimens of API 5L X52 steel. In this case too, in the solutions containing 25 ppm of the compounds of Examples from 1 to 9, no fractures occur after 720 hours.


Example 23

The test of stress corrosion by hydrogen sulfide of Example 21 is furthermore carried out at 80 °C instead than at the standard temperature of 25 °C, on specimens of API 5L X70 steel submitted to stress under constant load, inside solutions containing 25 ppm of the compounds of Examples 1 and 2 as the inhibitors.

Also in this case, after 720 hours, no fractures are observed.

Example 24

The corrosion inhibiting effect of the compound of Example 10 having the formula




is evaluated according to the method disclosed in Examples 11 - 20, but using solutions containing variable amounts of such a compound. The results obtained are reported in following Table III:

Table III

ppm	i_{corr} , $\mu\text{A/cm}^2$	i_{perm} , $\mu\text{A/cm}^2$
10	5.9	0.66
25	3.6	0.83
50	3.8	0.25
100	10.6	0.41

The effect of inhibition of stress corrosion by hydrogen sulfide of the compound of formula




is evaluated on the contrary by means of the standard test disclosed in Example 21, using a solution containing 25 ppm of the compound under test.

After 720 hours, no failures are observed.

Claims

1. Method for inhibiting the general corrosion and the stress embrittlement caused by hydrogen sulfide (SSC), both in the presence and in the absence of CO_2 , of manganese and low-alloy steels having different values of mechanical strength, used in the systems for drilling, producing, transporting and processing gas and petroleum, characterized in that a substance selected from among the group consisting of those substances as defined by the general formula:



wherein:

R_1 and R_2 , which may be equal to, or different from, each other, are a straight or branched, saturated or unsaturated, either substituted or non-substituted hydrocarbon chain of from 1 to 30 carbon atoms, or a one-ring or condensed two-ring, aromatic or heteroaromatic radical;

m is either 0 or 1; and

n is a numeral comprised within the range of from 1 to 30,

is added to the aggressive aqueous-organic mixture into contact with said systems.

2. Method according to claim 1, characterized in that R_1 and R_2 , the one independently from the other one, represent an aliphatic radical with an either straight or branched chain, containing from 1 to 30 carbon atoms, and, possibly, one or more unsaturations, or a one-ring or condensed two-ring heteroaromatic radical.

3. Method according to claim 1, characterized in that R_1 and R_2 , the one independently from the other one, represent an aliphatic radical with an either straight or branched chain, containing from 1 to 30 carbon atoms, or a condensed two-ring hetero-aromatic radical.

4. Method according to claim 1, characterized in that R_1 and R_2 , the one independently from the other one, represent an aliphatic radical with an either straight or branched chain, containing from 1 to 30 carbon atoms.

5. Method according to claim 1, characterized in that R_1 is a straight-chain aliphatic radical of from 1 to 30 carbon atoms, and R_2 is a quinolinyl radical.

6. Method according to claim 1 in which the compound(s) of formula (I) is/are used in an amount comprised within the range of from 1 to 500 ppm.

7. Method according to claim 6 in which said amount is comprised within the range of from 5 to 200 ppm.
8. Method according to claim 7 in which said amount is comprised within the range of from 15 to 100 ppm.

5

10

15

20

25

30

35

40

45

50

55

THIS PAGE BLANK (USPTO)

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 352 855 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **89201924.1**(51) Int. Cl.⁵: **C23F 11/14**(22) Date of filing: **21.07.89**(13) Priority: **29.07.88 IT 2155288**
23.12.88 IT 2309488(40) Date of publication of application:
31.01.90 Bulletin 90/05(54) Designated Contracting States:
AT BE CH DE ES FR GB GR LI LU NL SE(36) Date of deferred publication of the search report:
08.07.92 Bulletin 92/28(71) Applicant: **ENIRICERCHE S.p.A.**
Corso Venezia 16
I-20121 Milan(IT)(72) Inventor: **Cesari, Marco**
Via Ravenna 10/A
I-20097 San Donato Milanese Milan(IT)
Inventor: **Roggero, Arnaldo**
Via Libertà 72
I-20097 San Donato Milanese Milan(IT)
Inventor: **Rivola, Luigi**
Via Moro 21
I-20097 San Donato Milanese Milan(IT)
Inventor: **Demertzis, Yean**
Via Breno 4
I-20139 Milan(IT)(74) Representative: **Roggero, Sergio et al**
Ing. Barzanò & Zanardo Milano S.p.A. Via
Borgonuovo 10
I-20121 Milano(IT)(54) **Inhibitors of corrosion in high-strength and medium-strength steels.**

(57) A method is disclosed for the inhibition of general corrosion, and of stress corrosion by hydrogen sulfide in manganese and low-alloy, medium-strength and high strength steels, obtained by means of the use of compounds of formula:



EP 0 352 855 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 20 1924

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	US-A-2 836 557 (W.B. HUGHES) * Claim 1; table I *	1,2,6-8	C 23 F 11/14
X	EP-A-0 156 631 (DOW CHEMICAL) * Claim 1; pages 7,8 *	1,2,6-8	
A	US-A-3 432 527 (R.E. MALEC) -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 23 F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 23-03-1992	Examiner TORFS F.M.G.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 130 Q1.2 (P0401)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)